

Crystal Data: Triclinic. *Point Group:* $\bar{1}$. As highly elongated (on [001]) prisms with equant cross-sections, to 2000 μm , in sprays and parallel aggregates.

Physical Properties: *Cleavage:* Very good on {100}. *Tenacity:* Brittle. *Fracture:* Splintery. Hardness = ~ 5 D(meas.) = n.d. D(calc.) = 3.523 Water soluble and hygroscopic.

Optical Properties: Transparent to translucent. *Color:* Colorless, creamy white. *Streak:* White. *Luster:* Vitreous.

Optical Class: Biaxial (+). $\alpha = 1.686(2)$ $\beta = 1.690(2)$ $\gamma = 1.702(5)$ $2V(\text{meas.}) = 57(1)^\circ$

$2V(\text{calc.}) = 60^\circ$ *Orientation:*

	<i>a</i>	<i>b</i>	<i>c</i>
X	100.5°	92.0°	2.1°
Y	100.8°	2.1°	88.0°
Z	164.9°	89.1°	89.9°

Cell Data: *Space Group:* $P\bar{1}$. $a = 9.575(6)$ $b = 5.685(4)$ $c = 7.279(5)$ $\alpha = 89.985(6)^\circ$
 $\beta = 100.933(4)^\circ$ $\gamma = 101.300(5)^\circ$ $Z = 1$

X-ray Powder Pattern: Agua de Pau (also named Fogo volcano), São Miguel Island, the Azores. 2.954 (100), 3.069 (42), 2.486 (24), 3.960 (23), 2.626 (21), 1.820 (20), 2.195 (17)

Chemistry:	(1)		(1)
Ta ₂ O ₅	0.24	Nd ₂ O ₃	0.72
Nb ₂ O ₅	3.73	Ce ₂ O ₃	0.62
ZrO ₂	1.72	La ₂ O ₃	0.18
TiO ₂	7.48	Y ₂ O ₃	16.74
SiO ₂	29.81	FeO	0.64
Lu ₂ O ₃	0.29	MnO	2.74
Yb ₂ O ₃	0.87	CaO	13.89
Er ₂ O ₃	1.17	Na ₂ O	10.80
Dy ₂ O ₃	1.78	F	6.74
Gd ₂ O ₃	1.74	<u>-O=F₂</u>	<u>2.84</u>
Sm ₂ O ₃	0.41	Total	99.47

(1) Agua de Pau (also named Fogo volcano), São Miguel Island, the Azores; average of 10 electron microprobe analyses supplemented by FTIR spectroscopy; corresponds to (Na_{2.74}Mn_{0.15}) $\Sigma=2.89$ Ca₂[Y_{1.21}(La_{0.01}Ce_{0.03}Nd_{0.03}Sm_{0.02}Gd_{0.08}Dy_{0.08}Er_{0.05}Yb_{0.04}Lu_{0.01}) $\Sigma=0.35$ Mn_{0.16}Zr_{0.11}Na_{0.09}Fe²⁺_{0.07} Ca_{0.01}] $\Sigma=2$ (Ti_{0.76}Nb_{0.23}Ta_{0.01}) $\Sigma=1.00$ (Si_{4.03}O₁₄)O_{1.12}F_{2.88}.

Occurrence: In miarolitic cavities in a syenite xenolith in trachytic ejecta from a stratavolcano.

Association: Sanidine, astrophyllite, fluornatropyrochlore, ferrokentbrooksit, quartz, ferrokatophorite.

Distribution: From the flanks of Agua de Pau (also named Fogo volcano), São Miguel Island, the Azores.

Name: For the Fogo volcano, São Miguel Island, the Azores, where the first specimens were collected.

Type Material: Museo Regionale di Scienze Naturali di Torino, Torino, Italy (M/U 16800 and M/U 16801); the Royal Ontario Museum, Toronto, Ontario, Canada (M56826); and Muséum National d'Histoire Naturelle of Paris, France (MIN2015-003).

References: (1) Cámara, F., E. Sokolova, Y.A. Abdu, F.C. Hawthorne, T. Charrier, V. Dorcet, and J.-F. Carpentier (2017) Fogoite-(Y), Na₃Ca₂Y₂Ti(Si₂O₇)₂OF₃, a Group I TS-block mineral from the Lagoa do Fogo, the Fogo volcano, São Miguel Island, the Azores: Description and crystal structure. *Mineral. Mag.*, 81(2), 369-381. (2) (2018) *Amer. Mineral.*, 103, 660-661 (abs. ref. 1).