

Crystal Data: [Monoclinic, pseudo-orthorhombic] (by analogy to hydroxylherderite). *Point Group:* 2/m. Crystalline.

Physical Properties: Hardness = 5–5.5 D(meas.) = 3.02 D(calc.) = n.d. Fluoresces violet under UV; cathodoluminesces and phosphoresces pinkish orange under X-rays.

Optical Properties: Transparent. *Color:* Light green; colorless in transmitted light.

Luster: Vitreous.

Optical Class: Biaxial (-). *Orientation:* $r > v$, moderate. $\alpha = 1.556\text{--}1.59$ $\beta = 1.578\text{--}1.61$ $\gamma = 1.589\text{--}1.62$ $2V(\text{meas.}) = \text{n.d.}$ $2V(\text{calc.}) = 70^\circ$

Cell Data: *Space Group:* n.d. $Z = \text{n.d.}$

X-ray Powder Pattern: Cannot be distinguished from hydroxylherderite; similar to datolite.

Chemistry: (1) Electron microprobe analysis of a gemstone from “Brazil” shows F 7.0% (so with F > 5.86%, the series midpoint).

Polymorphism & Series: Forms a series with hydroxylherderite.

Occurrence: Probably from a complex granite pegmatite.

Association: n.d.

Distribution: Originally found in Germany, at Ehrenfriedersdorf, Saxony, but the analysis showing F > OH is suspect and any material from this locality seems unavailable. A gemstone from “Brazil” is the only known fluorine-dominant herderite proven by modern analytical methods.

Name: To honor Siegmund August Wolfgang von Herder (1776–1838), mining official, Freiberg, Saxony, Germany.

References: (1) Palache, C., H. Berman, and C. Frondel (1951) Dana’s system of mineralogy, (7th edition), v. II, 820–822. (2) Dunn, P.J. and W. Wight (1976) Green gem herderite from Brazil. *J. Gemmology*, 15, 27–28. (3) Leavens, P.B., P.J. Dunn, and R.V. Gaines (1978) Compositional and refractive index variations of the herderite – hydroxyl-herderite series. *Amer. Mineral.*, 63, 913–917.